

Article **COUGAR LOW**
Category **S3L CI SR FO**
Sizes **36 - 47**
Width **11**
Weight (half pair, sz 42) **510 gr**
Metal free **Yes**
Certification **CE**

UPPER	extremely resistant fabric, resistant to abrasion and tears, water-resistant and breathable
LINING	extremely breathable polyamide lining. It absorbs moisture quickly and ensures a greater comfort during the whole working day. Optimal resistance to abrasion and anti-bacterial
TOE CAP	non-magnetic toecap, from composite materials. 50% lighter than steel
ANTI-PERFORATION MIDSOLE	non-magnetic, perforation resistance composite fabric plate. It is 40% lighter and more flexible than steel plate and at the same time guarantees an optimal protection covering 100% of the foot surface. Certified EN 12568:2010
FOOTBED	insole PU 10mm expanded, covered with antibacterial fabric
SOLE	PU double density with optimal absorption of strains on the vertebral column thanks to the use of expanded PU midsole. Maximum stability

bdry

XLTOP
DEFENCE

Shield PRO

HSR



PREDATOR collection

	Requirements EN ISO 20345:2022	Test Results
UPPER		
Water Vapour Permeability	mg/cmq*h ≥ 0,8	4,2
Water Vapour Coefficient	mg/cmq ≥ 15	40,1
LINING		
Water Vapour Permeability	mg/cmq*h ≥ 2	11,1
Water Vapour Coefficient	mg/cmq ≥ 20	97,7
TOECAP		
Impact resistance: clearance under the toecap	mm ≥ 14	24
Compression resistance: clearance under the toecap	mm ≥ 14	19
ANTI-PERFORATION MIDSOLE		
Penetration resistance (EN ISO 12568:2010)	N ≥ 1100	≥ 1100
ELECTRICAL RESISTANCE		
- wet condition (85% relative humidity)	MΩ ≥ 0,1	19
- dry condition (30% relative humidity)	MΩ ≤ 1000	364
SOLE		
Abrasion resistance: relative volume loss	mm³ ≤ 150	42,5
Flexing resistance: cut growth	mm ≤ 4	0
Resistance to fuel oil: volume increase	% ≤ 12	1,7
Energy absorption of seat region	J ≥ 20	27
Coefficient d'adhérence de la semelle extérieure sur sol en acier lubrifié par glycérine	Talon ≥ 0,13 Plat ≥ 0,18	0,14 0,24
Coefficient d'adhérence de la semelle extérieure sol en céramique lubrifiée par détergent	Talon ≥ 0,28 Plat ≥ 0,32	0,60 0,80

Perf Italia Srl. All rights reserved. The data indicated in this sheet can be modified without notice following evolution in materials and products. Version 1.6

